



Commercial Grade Waterproofing Membrane

ProVention 363 Solvent-based

Description

ProVention 363 Solvent-Based Waterproofing Membrane is a tested and proven membrane for commercial applications.

Features / Benefits

- Creates a seamless membrane
- Effectively coats rough and porous surfaces
- Seals around fasteners

Uses

ProVention 363 S.B. membrane is ideal for new construction waterproofing of below-grade commercial walls of poured concrete. In addition, it can be used in horizontal applications such as parking garages, bridge decks, and plaza decking as well as retaining wall applications.

Equipment

For maximum output of the product, Mar-flex recommends the use of airless spray equipment. A pressure of 3000 psi is required to spray the membrane.

Coverage

Depending on porosity and roughness of surface, coverage rate for spray application should be 3.2 – 4 gallons per 100 ft². Final application milage should be as follows depending on the depth of the walls: On a 10' wall application, final application coat should be at a 100-mil wet membrane thickness. This will result in a minimum of an 80-mil dry thickness. On a 20' wall application, final application coat should be at a 120-mil wet membrane thickness. This will result in a minimum of a 100-mil dry thickness. On a 30' wall application, final application coat should be at a 140-mil wet membrane thickness. This will result in a minimum of a 120-mil dry thickness. The wet mil thickness can be determined by using a standard wet mil gauge.

General Requirements

Avoid application when inclement weather is present or imminent. Do not apply the ProVention S.B. membrane when the air temperature is below 0° F. Ensure that footings are exposed and free of any debris, loose material, wet/damp or frozen areas. Sweep the tops of footers to clear away debris and dry footings/walls. Walls must be set before applying the ProVention membranes. Make sure that all existing pipe, conduit or any other penetration through the wall are properly sealed on the outside with water plug, hydraulic cement or similar product. If penetrations are to be added after the spray application, it is still the applicators responsibility to ensure these areas are sealed. If this responsibility is passed onto the builder, inform the

builder they are responsible and inform them of the proper procedure to seal these areas.

Required Prep Work

Remove below grade wall ties inside the basement and out. Patch all outside below grade wall ties with the Mar-flex 362 Mastic or similar. Poured concrete walls must be free of voids and honeycombs. Any such areas, if present, should be covered with the Mar-flex Mastic or similar mastic. All brick ledges must be properly capped and sealed.

Application Information

When spraying ProVention S.B., the final recommended spray temperature of the material should be 100°F - 150°F.

Spray Installation/Vertical

Membrane application should be done a section of the wall at a time. Use multiple, uniform passes, alternating from horizontal to vertical. As work progresses check for thin spots and voids in the spray application. Re-spray any areas as necessary to obtain the required mil thickness. Determine the wet mil thickness by using a standard wet mil gauge. Application should be made to all below-grade basement walls. This includes any wall that would be considered a common wall to habitable/storage areas.

Application Note

Outgassing is a naturally occurring phenomenon of concrete that can produce bubbling or pinholes in liquid applied membranes. The bubbling or pinholes generally return to their normal state once the gas has evaporated. Installing the membrane either when the concrete temperature is falling or stable can reduce outgassing.

Horizontal Prep/Application

Horizontal surface should be dry and swept free of any loose debris and/or dust. Apply the ProVention 363 by spraying, brushing or rolling to the surface at a minimum of a 100 mil dry thickness. Allow to cure for approximately 3-4 hours. Membrane will not be fully cured which allows for adhesion of the "C" Drain 400 roll. Unroll "C" Drain placing gray side down. Unroll the next section placing the roll directly up against the end of the preceding roll. Join roll ends by peeling back the fabric and removing 4" of core. NOTE: All core joints must be covered by fabric overlay. Place end panels so that cores abut, then glue, tape or nail fabric overlap. Make cuts for any drains to allow water to be drained. Allow 24 hour set time before traffic is allowed. After completing installation of the "C" Drain 400, allow for a minimum of 24 hours set time and then pour desired thickness of concrete over the "C" Drain. Note: It is recommended to use 12" Geo Drain to remove the water that is drained through the "C" Drain 400.



Commercial Grade Waterproofing Membrane **ProVention 363 Solvent-based**

Optional Board Application

It is recommended that one of the following boards/rolls be applied after the application of the ProVention 363 S.B. when performing vertical applications. Shockwave 1" or 2", or the Geo-Mat™ Plus Drainage Roll, or the "C" Drain 150 should be installed immediately after spraying each section of the wall with the ProVention 363 membrane.

After building the membrane up to the required mil thickness, place the recommended drainage board/roll against the sprayed wall. Press firmly onto wall. The "C" Drain 400 is recommended for horizontal applications. Note: Please see the individual instruction sheet for the proper way to install the board or roll that you are using.

Backfilling/Drainage

Backfilling should begin no sooner than 24 hours after the installation of the ProVention S.B. Waterproofing System, but must be backfilled within 15 days. #57 Gravel or equivalent must be no less than 6" to 2' high at the base of the foundation and 1' in depth away from the foundation walls. Adequate interior and exterior foundation drainage at the base of the foundation walls or across any floors must be properly installed and working. Gutters and downspouts must be installed and functioning properly. Adequate drainage in landscaping beds adjacent to the foundation must be installed. Final grade must not extend above the waterproofing system and must slope away from the foundation at a minimum of 1/2" per foot for the first 12' from the structure.

Note: On vertical wall applications, Mar-flex recommends the installation of the C Drain 12" at the footer and at every 10' lift. This finishes the job and allows relief of hydrostatic pressure and helps assure water does not infiltrate through below-grade walls.

Packaging

ProVention 363 S.B. is available in 55 gallon drums.

Shelf-Life

When stored at temperatures between 20° - 100° F shelf life is unlimited in the original, unopened container.

Limited Warranty

Mar-flex Waterproofing & Building Products warrants this product to be free of defects in workmanship and materials only at the time of shipment from our factory. If any Mar-flex materials prove to contain manufacturing defects that substantially affect their performance, Mar-flex will, at its option, replace the materials or refund its purchase price. This limited warranty is the only warranty extended by Mar-flex with respect to its materials. There are no other warranties, including the implied warranties or

merchantability and fitness for a particular purpose. Mar-flex specifically disclaims liability for any incidental, consequential, or other damages, including but not limited to, loss of profits or damages to a structure or its contents, arising under any theory of law whatsoever. The dollar value of Mar-flex's liability & buyer's remedy under this limited warranty shall not exceed the purchase price of the Mar-flex material in question.

HEALTH AND SAFETY INFORMATION IS GIVEN IN THE MATERIAL SAFETY DATA SHEET AND THE PRODUCT DATA SHEET AVAILABLE FOR THIS PRODUCT. THESE SHOULD BE READ AND UNDERSTOOD BEFORE USING THIS PRODUCT.

Mar-flex Waterproofing & Building Products
500 Business Pkwy Carlisle, OH 45005
Ph-(800) 498-1411 | (513) 422-7285 |
Fax-(513) 422-7282
E-mail: info@mar-flex.com
Web-site: www.Mar-flex.com

ProVention 363 Solvent Base Spec Sheet

Property	Method	Results
Color		Black
Total Solids		70-75%
Application Method		Spray, Brush, Roller
Application Range		0° to 150°F
Elongation @ 70° F (21°C)	(ASTM D-412 Die C)	1672% min.
Crack Bridging Ability	(ASTM C-836)	10 cycles; without bond failure
Resistance to Hydrostatic Head Pressure	(Federal Spec TT-C-555B, Par 4.4.7)	Water Leaks: None Weight Gain: None
Total Cure Time		24 hrs.
Weight/Gallon		7.8 lbs. (3.4kg)
Coverage Rate		4-5 gal./100 ft²
Tensile Strength	(ASTM-C-719)	56.4 psi (331 kPa)
Water Vapor Permeance	(ASTM E-96)	Transmission: 0.11 grains/sf/h Permeability: 0.23 perms
Mold Growth/Bacterial Attack		No Degradation
Membrane/ Vertical		80 mil dry thickness
Membrane/ Horizontal		100 mil dry thickness
Adhesion to Concrete		No Adhesion Loss